

Enquiry

Bill of Quantities for  
Plasticoate roof coating  
Plasticoate Roof Coating PC Type  
System: Plasticoate Roof coating – dot adhesive method  
For repairable, bituminous roof areas

Pos.	Unit	Article / Description	Individual Price	Total Price
		Before using this product please note our systems recommendations for Plasticoate roof coating products		
		<u>Our address:</u> Plasti-Chemie GmbH Klopstockstr. 19 08525 Plauen Tel: +49 3741 55830 Fax: +49 3741 558327		
1.		roof preparation		
1.01	m <sup>2</sup>	roof area needs to be cleaned, rubble must be removed	_____ , _____	_____ , _____
1.02	m <sup>2</sup>	open bubbles and folds, to be cleaned and filled with Plasticoate Plastic-Cement	_____ , _____	_____ , _____
1.03	m <sup>2</sup>	stick together Poly-Star tissue with Roof Coating PC Type along roof edges and around large roof breaches	_____ , _____	_____ , _____
1.04.1	m <sup>2</sup>	Contingency Roof sheet will be sticked together dot by dot with Plasticoate Roof-Coating PC Type, 5 dots/m <sup>2</sup> , consumption: 0,6 kg/m <sup>2</sup>	_____ , _____	_____ , _____
1.04.2	m <sup>2</sup>	Contingency Bitumen sheets V60 S4 weld completely	_____ , _____	_____ , _____
1.05	m <sup>2</sup>	Sheets should overlap 10 cm. Overlap area will be coated with Plasticoate Roof Coating PC Type (1kg/m <sup>2</sup> ). Following sheets should be embedded in the still wet coating.		
		OR Welding with torch bitumen sheets V60 S4 that overlap 10 cm	_____ , _____	_____ , _____

Pos.	Unit	Article / Description	Individual Price	Total Price
			last page:	_____ , _____
1.06	piece	Contingency installation of a roof fan every 50 m <sup>2</sup>	_____ , _____	_____ , _____
1,07	m <sup>2</sup>	strengthen all overlaps, joints and roof breaches with Poly-Star	_____ , _____	_____ , _____
2.00		Plasticoate Roof-Coating		
2.10	m <sup>2</sup>	The whole roof area needs to be coated with a first coating (Plasticoate Roof- Coating PC Type; 1,5 kg/m <sup>2</sup> )	_____ , _____	_____ , _____
2.20	m <sup>2</sup>	One sheet polygamous tissue Poly-Star with 10 cm overlap embedded in first coating. Put on second coating that consists of a sheet Plasticoat Roof- Coating PC Type (1,5 kg/m <sup>2</sup> )	_____ , _____	_____ , _____
2.30a	m <sup>2</sup>	wet roof coating is to be littered with grit	_____ , _____	_____ , _____
2.30b	M <sup>2</sup>	OR after 6 month to be coated with 0,15 kg/m <sup>2</sup> Aluminium Roof Coating	_____ , _____	_____ , _____
		summary		
		preparation of the roof		
		Plasticoate roof coating		
		installation of the site		
		net price		_____ , _____
			%	_____
		VAT		_____ , _____
				_____
		total		_____ , _____